

Silica Sand Honeycomb Panel Technical Data

Dimensional Specification

1.1. Total thickness [mm]	20
1.2. Silica Sand thickness top cover sheet [mm]	2
1.3. Aluminum thickness back cover sheet [mm]	1
1.4. Thickness tolerance [mm]	± 0,2
1.5. Weight [kg/m ²]	10,5
1.6. Standard width [mm]	1000 / 1250 / 1500
1.7. Width tolerance [mm]	0 / + 2,0
1.8. Minimum / maximum length [mm]	1000 / 4000
1.9. Length tolerance [mm]	0 / + 3,0
1.10. Core	aluminum honeycomb

Silica Sand sheets

2.1. Silica Sand Surface	Silica Sand
2.2. Ultimate tensile strength, R _m [N/mm ²] ISO 6892-1:2009	81,1
2.3. Modulus of elasticity, E [N/mm ²]	15457
2.4. Anticorrosive pretreatment	Yes

Aluminum core

3.1. Aluminum alloy	3003
3.2. Compressive strength [MPa]	195
3.3. Core density [kg/m ³]	38,4
3.4. Cell size [mm]	9,5
3.5. Anticorrosive pretreatment	Yes

Mechanical properties

4.1. Moment of inertia, J [cm ⁴ /m] DIN 53293	35,9
4.2. Rigidity (theoretical value) EJ [KNcm ² /m] DIN 53293	55490
4.3. Section modulus, W [cm ³ /m] DIN 53293	32,7
4.4. Thermal resistance, R [m ² K/W] ASTM E1530-11	0,024
4.5. Thermal conductivity, λ [W/mK] ASTM E1530-11	0,833
4.6. Silica Sand thermal expansion [10 ⁻⁶ m/(m K)]	9,8
4.7. Temperature stability [°C]	-40 / +80

Fire classification

5.1. Building market: EN 13501-1	A2 – s1, d0
----------------------------------	-------------